

AOMT 123608 PETR LT 30

Material Group	Gr. N°	VDI Group	Material Examples*	Hardness	D.O.C. [mm]		Feed [mm/tooth]		V _c [m/min]		Optimal cutting conditions			
					min	max	min	max	min	max	D.O.C.	Feed	V _c	
Steel	Non-alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	11.0	0.13	0.22	190	330	2.0	0.15	250	
		2		190 HB									220	
		3		250 HB									200	
	Low alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	180 HB	0.5	11.0	0.11	0.18	150	240	2.0	0.13	200	
				230 HB									180	
				280 HB									150	
				350 HB									140	
	High alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	7.9	0.08	0.15	90	150	1.5	0.12	130	
				280 HB									120	
				320 HB									100	
				350 HB									80	
Stainless Steel	Austenitic	4	304, 316, X5CrNi18-9	180 HB	0.5	11.0	0.11	0.18	190	250	2.0	0.13	220	
				240 HB									190	
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.5	7.9	0.08	0.13	70	130	1.5	0.10	100	
				310 HB									90	
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	11.0	0.11	0.18	150	210	2.0	0.13	190	
				42 HRC									130	
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, No30B	150 HB	0.5	11.0	0.13	0.22	150	240	2.0	0.15	200	
				200 HB									180	
				250 HB									160	
	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.5	11.0	0.11	0.20	100	180	2.0	0.13	180	
				200 HB									150	
				250 HB									130	
High Temp. Alloys	Fe, Ni & Co based	9	31,32 Incoloy 800	0.5	7.9	0.08	0.13	25	45	1.5	0.10	32		
			33 Inconel 700									250 HB	30	
			34 Stellite 21									350 HB	30	
	Ti based	10	TiAl6V4	-	0.5	7.9	0.08	0.14	40	65	1.5	0.12	55	
37 T40	-	40												
Hardened Mat.	Steel	11	X100CrMo13, 440C,	45 HRC	0.5	3.9	0.07	0.13	40	80	1.0	0.09	60	
			G-X260NiCr42	50 HRC									55	
				55 HRC									50	
	Chilled Cast Iron	40	Ni-Hard 2	400 HB	0.5	3.1	0.07	0.13	40	80	0.8	0.09	50	
	White Cast Iron	41	G-X300CrMo15	55 HRC	0.5	1.2	0.07	0.10	30	60	0.5	0.08	40	
NF	Al (>8%Si)	12	25	AlSi12	130 HB	0.5	11.0	0.13	0.22	200	400	2.0	0.16	280