

## RDMT 0702 M0 LT 30

Material Group	Gr. N°	VDI Group	Material Examples*	Hardness	D.O.C. [mm]		Feed [mm/tooth]		V <sub>c</sub> [m/min]		Optimal cutting conditions		
					min	max	min	max	min	max	D.O.C.	Feed	V <sub>c</sub>
Steel	Non-alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	1.8	0.18	0.54	190	330	0.8	0.32	250
		190 HB		220									
		250 HB		200									
	Low alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	180 HB	0.5	1.8	0.15	0.43	150	240	0.8	0.28	200
		230 HB		180									
		280 HB		150									
		350 HB		140									
	High alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	1.3	0.12	0.37	90	150	0.6	0.25	130
		280 HB		120									
		320 HB		100									
		350 HB		80									
Stainless Steel	Austenitic	4	304, 316, X5CrNi18-9	180 HB	0.5	1.8	0.15	0.43	190	250	0.8	0.28	220
		240 HB		190									
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.5	1.4	0.12	0.31	70	130	0.6	0.22	100
		310 HB		90									
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	1.8	0.15	0.43	150	210	0.8	0.28	190
		42 HRC		130									
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, No30B	150 HB	0.5	1.8	0.18	0.54	150	240	0.8	0.32	200
		200 HB		180									
		250 HB		160									
	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.5	1.8	0.15	0.48	100	180	0.8	0.28	180
		200 HB		150									
		250 HB		130									
High Temp. Alloys	Fe, Ni & Co based	9	Incoloy 800, Inconel 700, Stellite 21	240 HB	0.5	1.4	0.12	0.31	25	45	0.6	0.22	32
		250 HB		30									
		350 HB		30									
	Ti based	10	TiAl6V4, T40	-	0.5	1.4	0.12	0.34	40	65	0.6	0.25	55
-	40												
Hardened Mat.	Steel	11	X100CrMo13, 440C, G-X260NiCr42	45 HRC	0.3	0.7	0.10	0.31	40	80	0.4	0.20	60
		50 HRC		55									
		55 HRC		50									
	Chilled Cast Iron	40	Ni-Hard 2	400 HB	0.3	0.5	0.10	0.31	40	80	0.3	0.20	50
	White Cast Iron	41	G-X300CrMo15	55 HRC	0.3	0.5	0.10	0.24	30	60	0.3	0.17	40
NF	AI (>8%Si)	12	AlSi12	130 HB	0.5	1.8	0.18	0.54	200	400	0.8	0.35	280

